

CONVERTEX

TESSUTI ELASTICI MADE IN ITALY

CONVERTEX SRL - Sede Legale: Via Volturmo 2/C, 00185 Roma - Sede Operativa: Via Colalillo, 86021 Bojano CB - P. Iva 02017750429
tel 0874.778050, 380.7591909 - fax 0874 782327 - numero verde 840 690309 - info@convertex.it - ww.convertex.it - cap. soc. € 200.000

SCHEMA TECNICA

DATA: 31/03/21

Fabric Category **TRANSFERT** (warp knit fabric – other: 6004 1000 25)

Fabrics in this category: **SIDNEY**

COMPOSIZIONE **ELASTAN** **18%**
COMPOSITION **PES MATT** **82%**

PESO **190 GM/M2 +- 5%** **ALTEZZA** **150 CM** **+ - 3%**
WEIGHT **WIDTH**

COLONNE/CM **26** **MAGLIE/CM** **42**
WALES/CM **COURSES/CM**

FINEZZA TELAIO **32 E** **ALTEZZA TELAIO** **130"**
MACHINE GAUGE **MACHINE WIDTH**

STABILITA' DIMENSIONALE LAVAGGIO 40°C TRAMA WEFT +2% - 4%
DIMENSIONAL STABILITY WASHING 40°C ORDITO WARP +2% - 4%

PROVE DINAMOMETRO ELETTRONICO TRAMA WEFT 110%+- 20%
ELECTRONIC DYNAMOMETER TESTS ORDITO WARP 150%+- 20%

MACCHINA: ACQUATI CARICO 20 N VELOCITA' 25 CM/MIN CAMPIONE 50x100 MM SCALA 0 - 20 N
MACHINE LOAD SPEED SAMPLE SCALE

PROVE ALLUNGAMENTO MANUALE TRAMA WEFT 120%+- 20%
HAND ELONGATION TESTS ORDITO WARP 160%+- 20%

U.P.F. (ultraviolet protection factor) bianco x stampa 40
AS/NZS 4399 1996 white for print



OEKO-TEX STANDARD 100 N° 953035.0

PLEASE TEST EACH DYE BATCH/DELIVERY BEFORE PRINTING, CUTTING, SEWING, ETC.

PER MIGLIORARE IL PRODOTTO, CI RISERVIAMO DI APPORTARE QUALSIASI MODIFICA IN QUALSIASI MOMENTO
WE RESERVE THE RIGHT TO VARY THE ABOVE DATA, AS AND WHEN NECESSARY, TO IMPROVE OUR PRODUCT